


Epecrete

Multipurpose, water based, epoxy moisture barrier

Packaging



Mixing



Application



Uses



Substrates

Concrete
Brick, Block
Cement render
Stone walls

Description

A multipurpose, water based, three-pack epoxy resin. **Epecrete** has excellent adhesion to most correctly prepared building surfaces such as brick, block, concrete and masonry.

Uses

A dampproofing membrane on concrete floors prior to floor coverings where moisture exceeds Australian Standards and to stop dampness in floors and walls of cellars, basements, etc. A primer for damp/immersed applications, smooth concrete and tiles.

Epecrete has a water vapour transmission (WVT) rate of 14g/m²/24 hours when properly applied and cured. All subsequent floor coverings or paint must have a higher WVT than **Epecrete** to ensure no vapour condensation build-up.

Coverage

3kg kit

Use	No. of coats	Coverage
Dampproofing	2	9m ²
Primer	1	18m ²

Specification

The epoxy resin shall be water based and when used for dampproofing shall have a WVT rate of 14g/m²/24 hours such as **Epecrete** manufactured by **Construction Chemicals** and be applied in accordance with the manufacturer's instructions.

Surface Preparation

The surface must be structurally sound and clean, free from laitance, dust, waxes, paint and other contaminants. Apply **Epecrete** to wood floated or broom finish concrete. Steel floated and contaminated surfaces must be suitably abraded with dustless shot blasting or grinding then washed thoroughly and surface water allowed to dry. Porous surfaces must be dampened prior to **Epecrete** application.

Mixing

Mix part A and B individually first, then mix part A and B together in a clean mixing container using a slow speed electric drill and mixing paddle for at least 3 minutes. Do not mix more than can be used in 30 minutes. Mix with powder to a uniform consistency.

Application

Apply with a brush or broom (for superior adhesion and improved penetration into the substrate), or a roller. On porous concrete, prior to applying **Epecrete**, dampen floor with water and avoid puddles. Apply the mixture in two thin coats, in different directions to avoid pin holes. Allow 24 hours before continuing work.

Recoat Time

2 hours at 25°C. Apply adhesives or toppings between 24 and 48 hours after second coat.

Pot Life

50 minutes @ 25°C @ 50% relative humidity.

Full Cure

7 days @ 25°C @ 50% relative humidity.



Adelaide Phone (08) 8243 7888

Darwin Phone (08) 8947 1811

Perth Phone (08) 9356 9999

Auckland Phone (09) 273 5444

Brisbane Phone (07) 3271 2944

Melbourne Phone (03) 9761 4711

Sydney Phone (02) 9756 3533

Kuala Lumpur Phone (603) 5122 2522

www.constructionchemicals.com.au