

Liquid Flash 2

Two-pack, fast drying, microfibre reinforced, waterproofing membrane

Packaging




Mixing



Application



Uses



Substrates

Concrete,
Brick, Block
Building boards
Roofs, Decks,
Basement, Pools,
Wet areas, Tanks

Description

Liquid Flash 2 is a two pack fast drying, microfibre reinforced, cement/acrylic flexible waterproofing membrane that is easily applied to form a resilient waterproof membrane over different building surfaces. **Liquid Flash 2** will remain pliable and elastic and will bridge cracks and smooth irregular surfaces. Internal wet areas must be waterproofed in accordance with AS3740 and AS4654.2 and local regulations. For more details refer to brochure titled 'Waterproofing Enclosed Shower Alcoves Prior to Tiling'.

Uses

A waterproofing membrane for roofs, balconies, swimming pools, retaining walls, planter boxes, internal wet areas (e.g. bathrooms, kitchens, laundries and toilets). For use on cement render, concrete, brick, block and building boards such as gypsum and cement sheeting on walls and compressed cement sheeting on floors.

Features

- Pre-reinforced
- Easy to apply
- Suitable for internal and external use, but must be covered with tiles, external coating, screed or earth
- Fast drying
- Swimming pools (prior to tiling)

Coverage (Approximate)

20L/20kg pack covers 14-18m² (2 coats), dry film thickness 1.5mm.

Performance Data

Conforms to AS/NZS 4858 Class 2 membrane

Tensile Strength (MPa)
AS/NZS 4858 2.93MPa

Elongation 184%
Modified CSIRO Moving Joint Test pass

Specification

The waterproof membrane shall be a two part cementitious/acrylic membrane that has a minimum tensile strength of 2.93 MPa and elongation 184% such as **Liquid Flash 2** manufactured by **Construction Chemicals** and shall be applied in accordance with the manufacturer's application instructions and AS3740 and AS4654.2 and local building codes and good trade practice.

Surface Application

The surface to be waterproofed must be structurally sound and free from dirt, dust, grease, paint, wax and other contaminants.

Cement sheet/plaster board and porous surfaces - Prime with **Primebond**.

Masonry - Render must be at least 7 days old, graded screed 7 days, concrete 28 days old and a minimum 20MPa.

Smooth concrete must be mechanically abraded and primed with **Super Prime**.

Swimming Pools and externally prime with **Primax**.

Mixing

Pour 4 litres of liquid into a mixing container and slowly add 4kg of powder. Mix using a slow speed electric drill (400-500rpm) and mixing paddle being sure to add powder to the liquid. Mix for 2-3 minutes – let stand for 5 minutes and remix until all lumps are dispersed and the mix is creamy. Adjust mix to suit user's preference. Do not mix more than can be used in the pot life time. Hand mixing is not recommended.

Bond Breaker and Reomat

At the junction of building surfaces, at wastes and over cracks, apply the bond breaker system to accommodate extremes in movement. The bond breaking system is the application of bond breaker tape centrally over the crack or junction, then the application of a thick coat of **Liquid Flash 2** 150mm wide centrally to these areas and bed in a 140mm wide Reomat into the wet **Liquid Flash 2**.

Membrane Application

Apply two coats. Apply the second coat at 90° to the first as soon as it is dry (recoat time is approximately 2 hours at 25°C). Apply each coat thickly (approximately 1.5mm wet) allowing it to flow rather than being brushed on. Use a soft brush for best results.

Pot Life

2 hours at 23°C @ 50% relative humidity.

Precautions

- The membrane will crack on the surface if excess powder is used. Do not thin or add filler
- Apply at temperature between 10-30°C

- At above 30°C temperatures the membrane exhibits thermoplastic characteristics
- Do not apply over surfaces subject to hydrostatic pressure or rising damp
- Protect from rain for 3-4 hours. Can be tiled on after 24 hours
- If a ponding test is required, ensure the membrane is allowed to cure for a minimum of 3 days, before ponding testing
- Not suitable for direct exposure to UV light and must be coated with **Deckgrip**, screed, an external paint, tiled over or used beneath ground
- Seal damp substrates with one coat of **Epecrete**
- Waterproofed areas must be sloped to a drain and water must not pond
- Swimming pools must be tiled

Curing

4 hours 23°C @ 50% relative humidity. Protect from rain for the first 4 hours. Cold damp conditions - increases curing time. Hot dry conditions - reduces curing time.

Immersed applications, i.e. pools, must be allowed to cure for 3 days @ 23°C @ 50% relative humidity or 5-7 days at 10°C before being put into use.

First Aid

If swallowed, do not induce vomiting. Give a glass of water and seek medical advice.

Clean Up

Clean up in water. Cured material with xylene solvent or similar.

Safety Precautions

Best used by an experienced tradesperson. Do not apply externally or on permanently damp surfaces. Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; www.constructionchemicals.com.au

Shelf Life

1 year



Adelaide Phone (08) 8243 7888

Darwin Phone (08) 8947 1811

Perth Phone (08) 9356 9999

Auckland Phone (09) 273 5444

Brisbane Phone (07) 3271 2944

Melbourne Phone (03) 9761 4711

Sydney Phone (02) 9756 3533

Kuala Lumpur Phone (603) 5122 2522

www.constructionchemicals.com.au

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.