
MULTIBOND MS50 - SEAL & STICK FC

Page 1 of 2

Technical Characteristics:

| | |
|--------------------------------------|------------------------|
| Base | Hybrid-polymer |
| Consistency | Paste |
| Curing System | Moisture Cure |
| Skin Formation (*) (20°C/65% R.V.) | Ca. 10 min. |
| Curing Rate (*) (20°C/65% R.V.) | 2 à 3 mm/24h |
| Hardness (DIN 53505) | 50 ± 5 Shore A |
| Specific Gravity (DIN 53479) | 1,67 g/mL |
| Maximum Deformation | ± 20 % |
| Elastic Recovery (ISO 7389) | > 75 % |
| Temperature Resistance (fully cured) | -40°C to +90°C |
| Elasticity Modulus 100 % (DIN 53504) | 1,00 N/mm ² |
| Tear Strength (DIN 53504) | 1,50 N/mm ² |
| Elongation at break (DIN 53504) | 400 % |

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates

Product:

Multibond MS50 Seal & Stick FC is a one component, high quality adhesive / single with high adhesive strength. It is fast curing and suitable for trafficable applications. It is based on hybrid-polymer.

Characteristics:

- good applicability and toolability
- high adhesive strength
- permanent elastic after cure
- paintable with waterbased paints
- Flexible sealant for trafficable internal & external movement joints
- Adhesive / trafficable sealant for the building and construction industry
- Fast curing sealant under water-based and acrylic waterproofing membranes (not solvent based)
- Adhesive / sealant for the industrial industry
- Adhesive / trafficable sealant for sanitary, bathroom and kitchen areas – resists mould growth
- Adhesive / trafficable sealant for natural stone (marble, granite, etc)
- Trafficable sealant for floors and perimeter joints
- Adhesive / sealant for roofing & guttering

Applications: continued

- Adhesive / sealant for caravan, bus, automotive, etc
- Adhesive / sealant around glass and glazing (non-structural)

Packaging & Colour:*600ml sausage – white, concrete grey and black***Shelflife:**

12 -18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Resistance to chemical agents:

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis. Poor resistance to aromatic solvents, concentrated acids, chlorinated hydrocarbons.

Substrates:*Nature:* clean, free of dust and grease*Priming:* Porous surfaces should be primed with Primer 150, Surface Activator may be used on non-porous surfaces.

We recommend preliminary compatibility tests previous to application.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.

MULTIBOND MS50 - SEAL & STICK FC

Revision: 05/07/2012**Page 2 of 2****Joint dimensions:**

Minimal width: 2mm (bonding)
5mm (joints)

Maximal width: 10mm (bonding)
30mm (joints)

Minimum depth: 5mm (joints)

Recommendation: width of joint = 2x depth of joint

Application:

Method: Manual- or pneumatic caulking gun

Application temperature: +5°C until +35°C

Cleaning: Fix ALL Cleaner immediately after application and before curing

Tooling: with soapy solution before skin formation

Repair with: MULTIBOND MS50 SEAL & STICK FC.

Health- and Safety Recommendation:

Apply the usual industrial hygiene.

Check the packaging for more information

Remarks:

- Multibond MS50 Seal & Stick FC may be painted, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application. The drying time of alkyd resin based paints may increase.
- Due to the wide variety of possible substrates, Soudal recommends a preliminary compatibility tests.
- This product can not be used as a glazing sealant.

Remark: The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith.

Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. In every case it is recommended to carry out preliminary experiments.