



# MAXGRIP®

## QUICK SETTING, FLUID ANCHORING MORTAR FOR CONCRETE AND MASONRY

### DESCRIPTION

MAXGRIP is a mixture of cements and selected special additives and aggregates. A pourable, cement-base, non-shrinking, quick-setting hydraulic compound.

### USES

Water/Sewer Management, Road/Rail, Construction Building/Swimming Pool Industry, Bridge Building, Councils, Heavy Industry, Mining, Steel, Defence Forces.

- Setting anchor bolts, rail posts, signposts.
- Parking meters, reinforcing rods and fixtures.
- Heavy machinery anchoring, hooks, pulleys.
- Park seats, bridge railings, partitions.
- Safety rails, hand rails, balustrades.
- Flag and light poles.

### ADVANTAGES

- Quick setting - 15 minutes.
- Stronger than concrete in one hour.
- Waterproof.
- Protects the fixture against corrosion.
- Grey Colour matching perfectly with concrete.
- Makes structurally sound bonds.
- Add water only - easy use.
- Waterproofs surface to which it is applied.
- Non-toxic.
- Odourless.
- Ideal for badly ventilated areas.
- Pourable.
- Contains no sulphur or iron particles, will not oxidise.

### APPLICATION

#### MORTAR PATCHING

##### Surface preparation.

Surface should be clean and free of dirt, grease and loose particles. Remove all damaged and unsound concrete to expose a structurally resistant substrate. Before applying **MAXGRIP**, wet the surface but do not leave free-standing water.

##### Mixing.

A 25 kg bag or pail of **MAXGRIP** is mixed with between 3,5 to 4,0 litres of clean water, depending on the ambient conditions and the consistency required, either manually or mechanically by low speed drill (400 – 600 rpm). **MAXGRIP** takes fifteen to twenty minutes to set, depending on the temperature. Mix only the amount of **MAXGRIP** that can be applied within eight to ten minutes.

##### Application.

For an optimum bonding, dampen the surface of the void with clean water, apply MAXGRIP into the void in successive layers up to 4 cm. each. Between layers, wait ten to fifteen minutes, depending on the temperature. Scratch the surface with the trowel to make the next layer adheres firmly. If the different layers become warm wet the surface with cold water.

##### Application conditions.

Do not apply with temperatures below 5 °C or if lower temperatures are expected during the 24 hours following the repair. Do not apply on frozen or frosted surfaces.

##### Curing.

For better curing once the job is finished cover with wet cloth to protect from high temperature and sun.

##### Cleaning.

Clean all tools and equipment immediately with water after use. Once **MAXGRIP** hardened it can only be removed by mechanical methods.



## ANCHORING AND GROUTING

Drill holes in sound concrete large enough for head and washer. If concrete is not sufficiently sound, drill the hole deeper. To increase the strength mushroom the base of the hole by tilting the drill. Blow or vacuum out excess dust and wet sides of hole to obtain proper bonding. Place anchor bolts, with washer into hole. Mix enough material to fill the hole. Mix with clean water in a water/MAXGRIP ratio of 1/ 6 approximately, about 3.75 to 4.25 litres of water per 25 kg. of material. In a small plastic bowl or other suitable container, mix to a pancake batter consistency. Pour a little **MAXGRIP** in the hole and work the bolt up and down a few times to eliminate any air bubbles. Pour in balance of mix from one side to ensure even flow. At 20°C, **MAXGRIP** will set in 15 minutes, complete cure after 60 to 90 minutes and will strengthen as it cures, so allow more curing time for heavy machinery and other large installations. For cold weather installations, heat hole before using **MAXGRIP**. Do not add antifreeze solutions to mixing water. Store material in a warm place.

### Test Data

- Compressive strength 7 days – 44.4 Mpa.
- Pullout strength 22 mm bolt in 80 mm hole = 109, 546 Kg/cm<sup>2</sup>.
- Set time I-Vicat - 15 minutes.

## Recommendations For Anchoring

Hole size should be 3 x the size of the bolt. This will ensure that the strength of the setting compares to the tensile strength of the mild steel bolt. Depth should be 5 x the diameter of the bolt or post.

### Packaging

25 Kg. pails 5 Kg. cans 2Kg pails



## CONSUMPTION

1 Kg. of MAXGRIP fills approx. 500 cm<sup>3</sup>

### Storage

12 months in its original unopened containers, in a dry covered place, protected from dampness and frost.

## Guarantee

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. **DRIZORO** reserves the right to introduce changes without prior advice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department.

© DRIZORO S.A. All rights reserved.

© **Scientific Waterproofing Products Pty Ltd. ABN: 155 659 948 All rights reserved.**

**Address: 4/92 Bryant Street, Padstow, NSW 2211, AUSTRALIA**

**Tel: +61 2 9771 0011 Fax: +61 2 9771 0111**

**Email: [info@scientificwaterproofingproducts.com.au](mailto:info@scientificwaterproofingproducts.com.au)**

**National Hotline: 1300 303 301 National Faxline: 1300 369 932**

**<http://scientificwaterproofingproducts.com.au/>**