

## Description

[Gripset C-1P](#) is a high performance 1 component flexible polymer cementitious membrane designed for a range of positive and negative waterproofing applications over concrete and masonry surfaces. Suitable for podiums, terraces, water tanks, water storage areas, basements, wet areas, cellar walls, lift pits, immersed and subterranean areas.

Based on unique polymer technology, [Gripset C-1P](#) possesses outstanding waterproofing and adhesion properties, with excellent resistance to frost, ageing, and salt water. Suitable for use over a range of building substrates, [Gripset C-1P](#) provides a unique advantage over 1 component cement based membranes as it not only forms a durable waterproof membrane but provides enhanced flexibility and excellent crack bridging properties over concrete/masonry cracks. Suitable for waterproofing the negative face of structures where access to the positive face is not possible, e.g. basements, underground walls etc, withstanding up to 15m head of pressure on the negative face.



## Features & Benefits

- Able to be used for both positive and negative waterproofing
- Waterproof, withstanding continuously wet and immersed environments
- Dries without cracking, low shrinkage
- 1 component, mixed on site with water, ready to use.
- Flexible and good crack bridging properties
- Tested up to 6 bar water pressure (60m head of pressure); positive side; tested to 1.5 bar (15m head of pressure) on negative side.
- Withstands UV light exposure
- Can be applied by brush, roller and trowel on horizontal and vertical surfaces without sagging. Able to spray apply
- Ability to apply over damp concrete
- Potable water approved
- Non-toxic

## Application

- [Gripset C-1P](#) is suitable for commercial, industrial and residential applications.

## Waterproofing Uses

- Basement walls, internal and external sides
- Lift pits
- Podiums, terraces, general external wet areas
- Water features, swimming pools
- Potable water storage facilities, retention and water tanks
- Waterproofing system over concrete blocks, brick, masonry and mortars where crystal treatments are not suitable
- Waterproofing under tiles and pavers in external areas
- Sandwich sealing between existing and new concrete toppings
- Planters, retaining walls, earth shelters

## Substrates

Substrates suitable for bonding [Gripset C-1P](#) over include:

- Concrete
- Render, screeds and general masonry surfaces
- Concrete blocks and clay brick
- Aerated concrete panels and blocks

For further information on suitable surfaces and substrates contact technical department of Gripset Industries for correct advice on surface preparation and suitability.

## Surface Preparation

Surfaces must be prepared thoroughly before commencing application. All substrates must be structurally sound, smooth, stable, and clean.

Highly dense, smooth/shiny and steel trowel finished concrete surfaces to be roughened or etched.

Rough surfaces and voids to be evened or filled first and all brick/block surfaces to be pointed flush. (refer to [Gripset 11Y](#) for concrete/masonry repairs). All general surface defects to be repaired.

Building surfaces must be constructed to manufacturer's recommendations and relevant building standards in force at time of membrane application.

All surfaces are to be free of sharp protruding objects, loose material, de-bonded coatings, curing membranes/agents, release agents, wax residues, foreign particles, laitance, algae and moss, grime, oils, animal fats or grease remains.

Structurally unsound layers and surface contaminants are to be mechanically removed by abrasive blasting, blast tracking, grinding or equivalent methods.

## Priming

[Gripset C-1P](#) must be applied onto a pre-dampened or primed surface: On porous concrete, masonry and mineral based substrates, surfaces can be pre wetted down with light water mist. When pre-dampening ensure there is no ponding or surface water before membrane application. Surfaces can be damp but must not have free water present when applying membrane.

**Gripset OP primer** – for non-porous, smooth and dense surfaces. Brush or roller apply primer to total surface area at a minimum coverage of 1 litre per 12m<sup>2</sup> and allow to dry for 1 hour

**Gripset 11Y slurry** – Highly porous surfaces including blockwork and over existing coatings. (suitability over existing coatings to be checked with Gripset Technical services before commencing) Mix [Gripset 11Y](#) in equal volumes to the following ratios: 1 part [Gripset 11Y](#) + 1 part Portland cement + 1 part fine wash sand, mix to form homogenous slurry. Brush apply to substrate at coverage of 1 litre per 3m<sup>2</sup>. Membrane is to be applied over primer slurry while primer is in a damp/wet state, i.e. “wet on wet” application

**Note:** Refer to data sheets for above primers before using

## Detailing

All critical areas such as joints, junctions, movement zones, penetrations drainage points and cracks are to be correctly sealed and detailed prior to membrane application.

<b>Voids, gaps and undulating surfaces in concrete/masonry</b>	Filled and evened with <a href="#">Gripset 11Y</a> repair mortar compound
<b>Static cracks up to 2mm:</b>	Filled with <a href="#">Gripset SB</a> , followed by <a href="#">Gripset RF reinforcement</a>
<b>Live cracks and cracks &gt; 1mm:</b>	Filled with <a href="#">Gripset SB</a> followed by <a href="#">Elastoproof Joint Band</a>
<b>Bond Breaker:</b>	<a href="#">Elastoproof Joint Band</a> to wall/floor junctions and wall/wall junctions.
<b>Movement or Expansion Joints:</b>	<a href="#">Elastoproof Joint Band</a>
<b>Penetrations, Pipes, Drain outlets:</b>	<a href="#">Elastoproof Collars</a> or <a href="#">Gripset SB</a> with <a href="#">Gripset RF Reinforcement</a> where collars cannot be utilised Butyl Squares over leak control flanges

## Membrane Application

### Mixing

1. [Gripset C-1P](#) consists of a 15kg bag dry powder. Membrane is formed by mixing 3.5-3.7litres of water to 15kg of powder.
2. Add 2/3 of the required water into a clean pail/drum. Slowly add the dry powder component to the water and mix using an electric stirrer with paddle attachment, ensuring the mixing of components is continuous while the powder is added. Continue mixing to form a lump free consistency. Then slowly add the 1/3 balance of water to the mixture until it is evenly dispersed and a homogenous consistency is formed.
3. Allow the mix to settle for 2-3 minutes then lightly re-stir before use. Pot life once mixed is 45-60 minutes; however, this may be reduced in warmer weather.

## Application and Coverage

The application of [Gripset C-1P](#) is at a minimum of 2 coats. Product can be applied by trowel, roller (low texture or medium-high nap), brush (slurry masonry brush) or spray unit.

- **For general waterproofing applications** – a minimum 1.5mm dried film thickness is required
- **For immersed applications** - a minimum 2mm dried film thickness is required
- **For preventing ingress of water under pressure** - a minimum 2.5mm dried film thickness is required
- **Coverage:** 1.25kg/m<sup>2</sup> per mm layer thickness
- Apply subsequent coats at different directions to the previous coat. Coverage is dependent upon surface condition and will vary accordingly as uneven and porous surfaces will require greater coverage to achieve the specified film thickness. For retainer walls and other underground applications Gripset recommends applying protection boards with Gripset BRW sealing strips to ensure membrane is not damaged.

**IMPORTANT:** For the blocking of vapours and negative entry of moisture on vertical surfaces, running or dripping water must be first treated with [Gripset C-Plug](#). Do not apply [Gripset C-1P](#) to surfaces where surface water is present.

## Installing Elastoproof Bond Breaker Joint Band

Measure and cut [Elastoproof Joint Band](#) for all wall/floor junction areas. Apply first coat of [Gripset C-1P](#) membrane to extending 150mm up walls and on to floors, and embed [Elastoproof Joint Band](#) into wet bed of liquid membrane, ensuring fabric edges are fully wet out and no air bubbles exist behind the fabric. Rear rubber section of Elastoproof Joint Band is not bonded to substrates. At sections where Joint Band is to be joined, a minimum 50mm overlap is required. Elastoproof Prefabricated Corners are available for both internal (90°) and external (270°) junctions, enabling [Joint Band](#) to overlap and avoid joint at critical areas. If Prefabricated corners are not used, [Elastoproof Joint Band](#) is to have bottom leg cut and folded; ensuring fabric is completely bonded with [Gripset C-1P](#)

## Sealing floor wastes and penetrations

For floor pipes protruding floors, [Elastoproof Collars](#) are to be fitted over the neck of the pipe, embedding fabric edges into wet bed of [Gripset C-1P](#) membrane. For sealing penetrations where Elastoproof product cannot be used, seal around base of penetration at abutment to substrate using [Gripset SB sealant](#) followed [RF Fabric](#) turned up the penetration and embedded into C-1P membrane.

For floor wastes that are finished level with the floor, the [Gripset C-1P](#) membrane with [Gripset RF Fabric](#) embedded is to be dressed down into the waste outlet at a minimum 50mm ensuring the perimeter of the pipe/substrate abutment is sealed.

For leak control flanges apply [Gripset SB](#) or compatible sealant around edges of flange at interface with floor substrate. [Gripset C-1P](#) membrane with [Gripset RF Fabric](#) embedded is to be applied over edges of flange at floor substrate abutment until total perimeter is sealed. Return the C-1P membrane down into flange. For alternative sealing option see [Elastoproof Butyl Squares](#).

When the detailing application has been completed apply [Gripset C-1P](#) membrane to the total floor area and to wall areas as required. A continuous seamless membrane should be the final finish to the total area upon completion of the waterproofing membrane application.

## Tiling & Surface Toppings

When tiling directly over [Gripset C-1P](#) in internal or external floor areas, polymer modified cement based adhesives must be used.

If applying a screed, render or concrete topping over [Gripset C-1P](#) it is recommended to incorporate [Gripset 11Y](#) as a proprietary bonding agent and water resistant additive. Alternatively see Gripset C-Bed polymer enhanced screed.

For use of other adhesives over [Gripset C-1P](#) contact the technical department of Gripset Industries for detail of compatibility.

Pre-mixed tile adhesives are not recommended for use over [Gripset C-1P](#).

**Note:** All tiling is to be carried out to AS3958.1 – 2007 “A Guide To The Installation of Ceramic Tiles”

## Storage conditions

- Best stored at room temperature.
- Avoid cold freezing conditions and off concrete floors.
- Do not store in direct sunlight.
- Shelf life: 12 months in unopened container

## Packaging

- 15kg bag

## Precautions

- Not to be used as a trafficable surface
- Do not apply to areas when rain is imminent
- Do not apply when surface temperature is below 5°C or above 30°C
- Not to be applied over glass or glazed surfaces
- Not to be used in areas where solvent or petroleum based products may be spilled
- All finish coatings over this membrane must be water based and solvent free
- Allow 10 days drying after final application for immersed conditions
- Exposure to water pressure, allow 7 days curing
- Safety Data sheet (SDS) available
- For further information contact technical department of Gripset Industries

## Clean up

- In water while wet.
- Once dried product needs to be removed mechanically or by solvent

## TECHNICAL DATA

<b>Appearance</b>	Grey powder
<b>Form</b>	When mixed – grey viscous slurry When dried – grey film
<b>Drying</b>	Tack Free: 15-20 minutes Re-coat: 90-120 minutes hours Dry film – 4-5 hours Tiling or toppings over: 24 hours Exposure to water pressure: 7 days curing Immersion: 10 days
<i>Based on normal ambient temperatures of 23°C and 50% RH</i> <i>*Temperature, humidity and porosity will vary dry times</i>	
<b>Mixing ratio</b>	3.5-3.7litres of water per bag
<b>Total Yield (mixed)</b>	12.5litres/18.5kg
<b>Specific gravity (mixed)</b>	1.5kg/litre
<b>Elongation</b>	85%
<b>Adhesion to concrete</b>	1.08MPa
<b>Tensile Strength</b>	1.1MPa
after 28 days immersion	0.89MPa
after freeze thaw cycle	0.74MPa
after exposure at 700C	0.9MPa
after caustic potash immersion (3% solution, 400C)	1.09MPa
<b>Crack Bridging (24 hour cycle)</b>	0.5mm
<b>Water Pressure</b>	1.5 bar, negative pressure 6 bar, positive pressure
<b>Water vapour diffusion - SD Value</b>	1.5

## Notes

It is recommended before commencing the application; that adhesion of products to be used (e.g. primers, membranes, coatings adhesives etc) is tested over a typical area of the prepared surface to ensure satisfactory adhesion. It is the responsibility of the applicator to carry this out and accept the substrate suitability before any application starts. Gripset Industries offers a service for pre testing adhesion to surfaces for large commercial areas or unusual substrates. For further details contact Gripset Industries. Details contained in product data sheets are general. For any situation or items not covered in this data sheet, it is the responsibility of the applicator to check with Gripset Technical Services before commencing the application. A written confirmation will then be issued by Gripset Technical Services.

## RLA Polymers

ABN: 89 004 709 915

Telephone: +61 (8) 8124-7300 or 1800 650 435

Email: [techenquiries@gripset.com](mailto:techenquiries@gripset.com)

## Product Disclaimer

This Product Data Sheet (PDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Gripset Industries does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.