

WATERSTOPPAGE®

GRANULAR SODIUM BENTONITE

DESCRIPTION

WATERSTOPPAGE is chemically treated, granular sodium bentonite used as a detailing accessory product for CETCO Waterproofing Systems. When wetted, WATERSTOPPAGE forms into a dense, low permeable material that combines with the sodium bentonite in the waterproofing products to form a seamless waterproofing membrane.

Mineralogical composition of WATERSTOPPAGE is a minimum 90% Montmorillonite with a maximum 10% native sediments and unaltered volcanic ash. Typical sieve analysis is 90% through a 20 mesh sieve and 10% through a 200 mesh sieve. Free swell rating of WATERSTOPPAGE is: two grams sifted into deionized water swells to occupy a minimum volume of 16 cc.

APPLICATIONS

WATERSTOPPAGE is used to fill cavities and voids in the substrate prior to installing the main bentonite waterproofing course. It is also used to seal around slab penetrations to form a continuous waterproofing system. A fillet of WATERSTOPPAGE can be poured at the footing/wall junction to provide additional waterproofing protection. A 1/8" (3 mm) thick layer of WATERSTOPPAGE is also applied to the top of tunnels and earth-covered roofs prior to the main waterproofing material course. WATERSTOPPAGE is not an expansion joint sealant.

PACKAGING

WATERSTOPPAGE is packaged in 50 lb. (22.6 kg) bags; 40 bags per pallet. One bag equals approximately 0.83 cubic feet.

INSTALLATION

Remove dirt and other debris from area to receive WATERSTOPPAGE. Cut a corner of the bag for easy, directional control of product placement. Place as required around penetrations, footings and other details.

Limitations: WATERSTOPPAGE should not be applied in standing water or during precipitation. WATERSTOPPAGE is intended for below-grade waterproofing applications. Product requires proper confinement. Confining soils should be compacted to a minimum 85% Modified Proctor density.

SAFETY

Use only with adequate ventilation and avoid breathing dust. Workers should wear approved breathing apparatus, protective clothing and eye protection. Avoid skin and eye contact. In the event of contact, wash immediately. Do not ingest. Refer to MSDS for other warnings and safety information.

TYPICAL CHEMICAL ANALYSIS	
CHEMICAL	PERCENTAGE
Silica (SiO ₂)	61%
Alumina (Al ₂ O ₃)	19%
Iron Oxides (Fe ₂ O ₃)	4%
Magnesia	2%
Soda	3%
Lime	2%
Trace Elements	3%
Water (crystal)	6%

TYPICAL APPLICATION RATE ONE BAG - 50 LBS (22.6 KG)	
APPLICATION	TYPICAL RATE
Wall/Footing Fillet 1-1/2" (38 mm)	30 lin ft (9.1 lm)
Roof Deck Layer 1/8" (3 mm) thick	70 sq ft (6.5 sq m)

North America: 847.851.1800 | 800.527.9948 |

© 2014 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. CETCO accepts no responsibility for the results obtained through application of this product. CETCO reserves the right to update information without notice.

UPDATED: SEPTEMBER 2013

TDS_WATERSTOPPAGE_AM_EN_201309_v1

CETCO®
OUR STANDARDS. YOUR PEACE OF MIND.
A Minerals Technologies Company