

Technical Data Sheet

- UV Stable
- Trafficable
- 2-Coat System
- Elastomeric
- Superior adhesion
- Podiums
- Balconies
- Roof tops
- Plant room floors
- Easy to apply

Pasco Construction Solutions P/L
13 – 15 Brighton Street
Richmond Vic 3121
Ph: 03 9429 9111
Fax: 03 9429 6111

Aquaproof 115 UV

UV Stable, trafficable polyurethane membrane coating system

Description

Aquaproof 115UV is a complete, moisture curing elastomeric polyurethane membrane system. Once cured it forms a tough, highly flexible rubber membrane, exhibiting tenacious adhesion to a variety of substrates. **Aquaproof 115UV** is a high strength, puncture resistant, monolithic, seamless waterproof membrane with the added advantage of being trafficable and U.V stable.

Features/Benefits

- U.V Stable
- Self Levelling
- Trafficable
- Easy to apply
- 450% Elongation
- Chemical resistant*
- Seamless
- Crack bridging
- Fast curing
- Superior adhesion

Uses

- Roof tops
- Podiums
- Balconies
- Walkways
- Plant Rooms

Substrate Preparation

- All surfaces must be clean, dry, sound and free from dust, oil, rust, plaster dust, cement droppings, protrusions, old sealant or any other contamination. Surfaces must be free from release and curing agents, please contact Pasco for further information.
- Metal surfaces shall be clean and free of any rust, dirt and grease. Rusted surfaces must be wire brushed or sandblasted and treated with an appropriate rust converter. Metal surfaces must be wiped clean with Pasco Xylol prior to application of primer.

Priming

- Using Aquaprime PU Primer or Aquaprime WBE prime entire substrate at required coverage rates and allow to dry.
- Install a minimum 12x12mm fillet/cove using PascoFlex PU25 polyurethane sealant to all internal/external corners. Seal all lap joints, floor penetrations, floor wastes, countersunk screws, etc.

Application

- Aquaproof 115UV should be mixed to ensure no settlement is in the bottom of the pail. Mix for approx 3-5 minutes using a low speed drill.
- Using a brush apply a detail coat (approx 200mm) of Aquaproof 115UV to all lap joints, internal corners, hobs, floor wastes, floor penetrations.
- Using a brush, roller or a notched squeegee, apply one coat of Aquaproof 115UV over the entire area at the required coverage rates.
- Allow Aquaproof 115UV a minimum of 24 hours curing, prior to applying a second coat of Aquaproof 115UV.
- If Aquaproof 115 UV is not top coated within 4 days, the surface must be solvent wiped with Xylol.
- If a non slip surface is required a light broadcast of sand (16/30 grade) is required in the first coat prior to curing.

Curing

Do not apply when rain exposure is likely within 24 hours of application. Full cure is achieved after 3 days at 25°C and 50% RH. Curing time is dependent on temperature and humidity.

Coverage

- Apply Aquaprime PU Primer at approx. 7 - 9m² per litre.
- Apply Aquaproof 115UV at 0.8kg per m² per coat Dry film thickness of 1mm.

Precautions

- Do not apply below 5°C
- Not to be used for waterproofing of chlorinated swimming pools.
- Not to be applied on damp substrates
- Not to be applied on unsound substrates.

Health and Safety

Keep out of reach of children. Wear suitable protective clothing, gloves and eye/face protection. Uncured sealant may cause skin, eye and respiratory system irritation. Use only in well ventilated areas.

In case of contact with eyes, rinse immediately with plenty of water and contact a Doctor or Poisons Information Centre (**Ph 13 11 26**). In case of skin contact, wash affected area with hand cleaner followed by soap and water.

Material Safety Data Sheets must be read and understood prior to using **Aquaproof 115 UV**.

Packaging

- Aquaprime PU Primer is available in 5lt & 20lt drums.
- Aquaprime WBE is available in 8lt & 20lt kits.
- **Aquaproof 115UV** is available in 25kg pails.

Colour

Pasco **Aquaproof 115UV** is available in Grey.

Shelf Life

12 months minimum, when stored in cool, dry, original containers in conditions below 25°C.

* Please contact Pasco for further information

Property	Test Method	Result
Viscosity (Brookfield)	ASTM D2196-86 @ 25C	3000-6000
Specific weight	ASTM D1475 DIN53217 @20°C	1.3 – 1.4
Flash Point	ASTM D93 Closed Cup	42
Tack Free Time @ 25°C		4
Recoat Time		6 - 24
Tensile strength @ break 23°C	ASTM D412 DIN 52455	55 kg/cm ³
Service Temperature		-40 to 80°C
Max temp. short time shock		200°C
Thermal Resistance (100 days @ 80°C)	EOTA TR011	Passed
Hardness (Shore A)	ASTM D2240 DIN 53505	75
Elongation @ 23°C	ASTM D412 DIN 52455	>450%
Water vapour transmission	ASTM E96	0.8 gr/m ² .hr
Adhesion to concrete	ASTM D4541	>20 kg/cm ²
QUV Accelerated Weathering Test (4hr UV @ 60°C (UVB lamps) 7 4hr COND @ 50°C)	ASTM G53	Passed 2000hrs

Pasco Construction Solutions Pty Ltd warrants its' products to be free of defects and faulty manufacture and are sold subject to its standard terms and conditions of sale, which are available upon request. All endeavors have been made to ensure the information provided in this technical data sheet is accurate and correct, however as the use of this material is beyond the supplier's control, liability is limited to replacement of material proven faulty. It is the responsibility of the purchaser to ensure that the product is suitable for the specific application and that it is applied in accordance with the suppliers' recommendations.